TECHNICAL DATA SHEET



SANVO High grade RTV Silicone Gasket Maker Silver



This product is specially designed for high-strength, heavy-duty cars or trucks. Oil resistance, water resistance, aging and environmental protection. The temperature resistance range is -60°C \sim 280°C, and the pressure can be greater than or equal to 15MPa.

Applications

SANIO室和

多今景·93g

Suitable for sealing and anti-vibration of mechanical parts of various high-grade cars, large trucks, motorbikes, etc.

Widely used in the assembly and repair of mechanical, electronic, chemical equipment.

Features

- Excellent elasticity
- Excellent oil resistance
- SILVER, Metallic shine
- Neutral and eco-friendly
- Temperature resistance -60° C to 280° C

Typical Properties

Composition Organic silicone rubber, filler, metal powder,

special elasticity reinforcing agent

Appearance Silver paste

Glossiness, Gs $\geqslant 10$

Surface drying time, min $\leq 15 (25 \,^{\circ}\text{C}, 50 \sim 75\%\text{RH})$

Consistency, cm $9.3 \sim 10.3$

Curing speed, mm/24h $\geq 2.5 (25^{\circ}\text{C}, 50 \sim 75\%\text{RH})$

Tensile elongation rate, % $\geqslant 250$

Tensile strength, MPa $\geqslant 0.7$

Mass loss rate, % (200°C, 1h) ≤ 7

Shore hardness, HA \geqslant 33

Density, g/ml $1.30 \sim 1.40$

Extrudability, ml/min ≥45

Shelf life 12 months

Web: http://www.sanvochemicals.com

TECHNICAL DATA SHEET





Instructions

- 1. Clean and dry the bonding surface.
- 2. Glue into an uninterrupted rubber ring (gluing must also be applied around the screw hole), and assemble it together.
- 3. It is fully cured in 24h at room temperature (25 $^{\circ}$ C), and the curing time must be prolonged at low temperature.

Precautions

- 1. Storage and construction must be in a ventilated and fireproof place to prevent children from contacting this product.
- 2. If your eyes accidentally come into contact with uncured sealant, you must wash it with plenty of water in time and ask a doctor for help.
- 3. Prevent the displacement of the construction joint surface before the glue is solidified.

Tips

Since the conditions and methods of using this product are beyond our control, users must decide on their own the applicability of the product and the most appropriate method of use. This product is only a guarantee for compliance with relevant standards, and no other express or implied guarantees are made.

Packing/Size

Content: 50g & 93g 50g×100pcs/carton 93g×80pcs/carton